



# Versaflex™ VDT 5110-80N

## Thermoplastic Elastomer

### Key Characteristics

Product Description	
Versaflex™ VDT 5110-80N is a vibration and impact damping TPE formulated to bond to polar resins including Polycarbonate (PC), ABS, PC/ABS, and Copolyester	
General	
Material Status	· Commercial: Active
Regional Availability	· Africa & Middle East · Europe · Asia Pacific · Latin America · North America
Features	· Good Adhesion · Vibration Damping
Uses	· Appliance Components · Flexible Grips · Power/Other Tools · Automotive Applications · General Purpose · Soft Touch Applications · Consumer Applications · Overmolding · Sporting Goods
RoHS Compliance	· RoHS Compliant
Appearance	· Natural Color
Forms	· Pellets
Processing Method	· Extrusion · Injection Molding

### Technical Properties 1

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.05	1.05	ASTM D792
Molding Shrinkage - Flow	0.015 to 0.023 in/in	1.5 to 2.3 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress 2, 3 (100% Strain, 73°F (23°C))	250 psi	1.72 MPa	ASTM D412
Tensile Stress 2, 3 (300% Strain, 73°F (23°C))	400 psi	2.76 MPa	ASTM D412
Tensile Strength <sup>23</sup> (Break, 73°F (23°C))	825 psi	5.69 MPa	ASTM D412
Tensile Elongation 2, 3 (Break, 73°F (23°C))	740 %	740 %	ASTM D412
Tear Strength 2 (73°F (23°C))	161 lbf/in	28.2 kN/m	ASTM D624
Compression Set (73°F (23°C))	21 %	21 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	80	80	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec <sup>-1</sup>	60.3 Pa·s	60.3 Pa·s	
392°F (200°C), 11200 sec <sup>-1</sup>	11.5 Pa·s	11.5 Pa·s	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	125 to 140 °F	51.7 to 60.0 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.030 %	0.030 %
Suggested Max Re grind	20 %	20 %
Rear Temperature	340 to 360 °F	171 to 182 °C
Middle Temperature	360 to 410 °F	182 to 210 °C

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection	Typical Value (English)	Typical Value (SI)
Front Temperature	370 to 420 °F	188 to 216 °C
Nozzle Temperature	380 to 430 °F	193 to 221 °C
Mold Temperature	55.0 to 85.0 °F	12.8 to 29.4 °C
Back Pressure	0.00 to 50.0 psi	0.00 to 0.345 MPa

**Injection Notes**

Color concentrates based on Versaflex™ VDT 5110-50N are most suitable for coloring Versaflex™ VDT 5110-50N. Typical loadings for color concentrates are 1% to 4% by weight. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex™ VDT 5110-50N with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex™ VDT 5110-50N has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Suggested Dewpoint: -40°F

Injection Speed: 0.5 to 2 in/sec

1st Stage - Boost Pressure: 500 to 1000 psi

2nd Stage - Hold Pressure: 20-60% of Boost

Hold Time (Thick Part): 2 to 4 sec

Hold Time (Thin Part): 1 to 2 sec

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> Die C

<sup>3</sup> 2 hr

**CONTACT INFORMATION****Americas**

United States - Avon Lake  
+1 440 930 1000

United States - McHenry  
+1 815 385 8500

**Asia**

China - Guangzhou  
+86 20 8732 7283

China - Shenzhen  
+86 755 2969 2360

China - Suzhou  
+86 512 6823 26587

China - Suzhou  
+86 512 6265 2658

Hong Kong -  
+852 2690 5315

Taiwan - Yonghe City,  
+886 9396 99740, +886 2929 1125

**Europe**

Germany - Gaggenau  
+49 7225 6802 0

Spain - Barbastro (Huesca)  
+34 974 310 314



*Beyond Polymers.*

*Better Business Solutions.*

SM

www.polyone.com

**PolyOne Americas**

33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE

**PolyOne Asia**

No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 2012, China  
+86 21 5080

**PolyOne Europe**

6 Giällewee  
+352 269 050 35

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.